

PRODUCT HIGHLIGHTS

4361-F, 4363-F, 4364-F Quick Dry Rubberized Undercoat

DESCRIPTION:

Quick Dry Rubberized Undercoat is a rapid-drying highly protective automotive coating for autobody interiors, underhood and underbody applications. Resists abrasion and inhibits rust as it seals out dust and moisture. Deadens sound. Excellent adhesion to painted and unpainted surfaces.

PRODUCTS:

4361-F Quick Dry Rubberized Undercoat, Gallon (3.78 L), 2/case
4363-F Quick Dry Rubberized Undercoat, 24 oz. aerosol (710 ml), 6/case
4364-F Quick Dry Rubberized Undercoat, Quart (0.946 L), 6/case



SURFACE PREP:

Clean with SCAT 6311, Speedi SCAT 6321 or Aqua SCAT 2 1391/1394.



MIX RATIO:

Ready to spray.

*See next page for more detailed product application. See website for this document in other languages.
Vea la página siguiente para un uso más detallado del producto. Vea el Web site para este documento en español.
Voir la prochaine page pour une application plus détaillée de produit. Voir le site Web pour ce document en français.*

PRODUCT DATA

4361-F, 4363-F, 4364-F

Quick Dry Rubberized Undercoat

SUITABLE SUBSTRATES:

Painted or primed steel and aluminum

SURFACE PREPARATION:

Clean with SCAT 6311, Speedi SCAT 6321 or Aqua SCAT 2 1391/1394.

APPLICATION:

Aerosol: Shake well.

1. Wash and solvent clean surface to remove all rust, dirt and grease using SCAT 6311, Speedi SCAT 6321 or Aqua SCAT 2 1391/1394.
2. Hold can in an upright position and spray 8-10 inches from surface, using steady light strokes. Several light coats will produce a better finish than one heavy coat.
3. Remove overspray with Acry Solvent 9783/9784.
4. May be topcoated after one hour.



Quart/Gallon: Stir thoroughly before use. Wash and solvent clean surface to remove all rust, dirt and grease.

1. Apply with a shutz gun, using the gun manufacturer's recommended air pressure.
2. Allow to dry at least 4 hours before painting. Thoroughly clean gun with Acry Solvent 9783/9784 immediately after use.
3. May be topcoated after an hour.

NOTE: This product contains asphalt which may stain light colored topcoats.

TECHNICAL DATA:

APPEARANCE: Black
SHELF LIFE: 1 year unopened

REGULATORY:

Category: Underbody Coating	Individual Component 4361-F & 4364-F
VOC Actual	2.74#/gal (328 g/l)
VOC Regulatory	3.58#/gal (429 g/l)
Weight % of Volatiles	55.78
Weight % of Water	0.1
Weight % of Exempt Compounds	20.08
Volume % of Exempt Compounds	23.35
Density of Material #/gal	7.69
Category: Undercoating	4363-F
VOC Content	<40% by weight

See website (www.tat-co.com) for this document in other languages.

Vea el Web site (www.tat-co.com) para este documento en español.

Voir le site Web (www.tat-co.com) pour ce document en français.

4361-F, 4363-F, 4364-F

Quick Dry Rubberized Undercoat

TECHNICAL TIPS:

For best results, thoroughly clean all surfaces prior to applying.

ADVANTAGES:

- Fast drying, easy to apply
- Excellent abrasion resistance
- Aerosol package requires no clean-up
- Retains black color
- Seals out dust, fumes, moisture, heat and cold
- Won't sag or run
- Dries completely, yet remains flexible

COMPETITION:

3M 08883
Car System 126.029

Wurth 893075/51
Rubberseal RS532

Dominion SS 240040