



DRIVING SURFACE PERFECTION™

UP7061 STRONGHOLD FILLER FOR PLASTIC

Description

With 7061 Flexible High Density Filler UP7061, skip the gun, cartridge and tip. Fix road rash, "hole throughs", and other flexible repairs with 7061 Flexible High Density Body Filler. Versatile enough to use on a variety of substrates, and specially designed for flexible plastics.

Health and Safety Statement

FOR PROFESSIONAL USE ONLY. Read full instructions before use. **IMPORTANT:** This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local distributor or via the U-POL website at WWW.U-POL.COM. U-POL disclaim any liability where the user does not wear the recommended personal protective equipment.

Surface preparation and instructions for use

7061 Flexible High Density Filler UP7061 can be used on all plastics provided that the following preparation is undertaken:-

- Clean all areas around the repair with soap and water. Then clean the repair area using a waterbased degreaser like UP2002 **System 20** Waterbased Degreaser; wipe dry with lint free cloth or blow off with clean compressed air.
- Sand repair area to remove paint and prepare plastic. Flexible plastics: sand with P80 grit. Rigid plastics: sand with P80 - P180 grit. Blow off area with clean compressed air.
- Apply **GRIP#4 1K Universal Adhesion Promotor UP0799** when working with TPO. Spray 1-2 light, even coats onto plastic surface. Allow to dry 10-15 mins air dry or 5-10 mins at 140°F.

Mixing ratio

Mix 100% by weight 7061 Flexible High Density Filler UP7061 with 2% by weight included U-POL hardener for polyester filler. Apply in thin coats, using firm pressure to reduce pinholes.

Pot life

Once mixed, approximately 5 minutes at 68°F with 2% hardener.

Tools

Clean mixing board, like Onion Board™ Multi-Layered Mixing Palette UP0737, and body filler spreader.

Drying time

Sandable after 15-20 minutes at 68°F. Blow off panel to remove sanding dust. DO NOT wipe with lacquer thinner or other solvents.

Over-painting

7061 Flexible High Density Filler UP7061 filler can be over-painted with most paint systems which are suitable for coating plastics.

Product code

7061 Flexible High Density Filler UP7061 - 600ml / 1000g tin.

U-POL US, Inc., 108 Commerce Way, Stockertown, PA 18083

Tel: (800) 340 7824; Fax: (800) 787 5150

Email: sales-us@u-pol.com Website: www.u-pol.com